

ALUMINUM SHEET THICKNESS TOLERANCES (INCHES±)

BY ALLOY GROUP AND WIDTH RANGE

Nom. Thick.	18.01 - 36.00		36.01 - 48.00		54.01 - 60.00		Weight Per Square Foot	
	1100 3003 3105 5005	2024 5052 6061 7075	1100 3003 3105 5005	2024 5052 6061 7075	1100 3003 3105 5005	2024 5052 6061 7075		
0.025	0.002	0.002	0.0025	0.0025	0.003	0.004	.3492 .3528	.3564 .3636
0.032	0.002	0.002	0.0025	0.0025	0.0035	0.005	.4472 .4518	.4564 .4556
0.040	0.0025	0.0025	0.003	0.003	0.004	0.005	.5587 .5645	.5702 .2518
0.050	0.003	0.003	0.004	0.004	0.005	0.006	.6984 .7056	.7128 .7272
0.063	0.003	0.003	0.004	0.004	0.005	0.006	.8798 .8889	.8979 .9161
0.71	0.003	0.003	0.004	0.004	0.006	0.006	.9894 .9996	1.010 1.030
0.080	0.003	0.0035	0.004	0.004	0.006	0.006	1.116 1.127	1.139 1.162
0.090	0.003	0.0034	0.004	0.004	0.006	0.0066	1.261 1.274	1.287 1.313
0.100	0.004	0.004	0.005	0.005	0.007	0.007	1.397 1.411	1.426 1.454
0.125	0.0045	0.0045	0.005	0.005	0.007	0.007	1.746 1.764	1.782 1.818
0.160	0.006	0.006	0.008	0.008	0.009	0.009	2.658 2.685	2.713 2.767
0.190	0.007	0.007	0.009	0.01	0.011	0.011	2.231 2.254	2.277 2.323

MILL STEEL

C O M P A N Y

WWW.MILLSTEEL.COM